

**Amendments to the Specification:**

Please replace paragraph [0009] with the following amended paragraph:

**[0009]** Premixes according to the invention are composed of:

- a) Polyol. Preferably a polyether polyol and/or a polyester polyol is used.
- b) 4 to 35% by weight, preferably 10 to 15% by weight, blowing-agent mixture. In addition to HFC365mfc, the blowing-agent mixture contains at least 5% by weight, preferably ~~at least~~ 7% by weight, of a further fluorohydrocarbon, preferably HFC134a, HFC227ea or HFC245fa; and
- c) 10 to 20% by weight, preferably 10 to 15 % by weight, of a phosphorus compound, preferably triethyl phosphate or tris-chloroisopropyl phosphate.